

Microneedles: An Innovative Method to Enhancing Skin Permeation

Dr. Shivendra Agarwal^{*1}, Dr. Girendra Kumar Gautam², Raghvendra Misra³, Pushpendra⁴

¹Department of Pharmacy, Vivekanand College of Pharmacy, Bijnor U.P. India

²Shri Ram College of Pharmacy, Muzaffarnagar U.P. India

³Teerthanker Mahaveer College of Pharmacy, TMU, Moradabad, U.P. India

⁴Department of Pharmacy, Vivekanand College of Pharmacy, Bijnor U.P. India

***Corresponding Author**
Dr. Shivendra Agarwal

Email: agarwalshivacsr@gmail.com

Article History

Received: 11.06.2023

Accepted: 15.07.2023

Published: 29.07.2023

This is an open access article under the
[CC BY-NC](#) license



Abstract: Transdermal management offers an avenue for delivering medications profoundly throughout the circulatory system and directly over the top layer of skin. It appeals to an array of experts because to its various biological advantages. The protective function within the stratum corneum poses an obstruction to medication distribution. Recent study data has shown that using microneedles to make the skin more permeable greatly improves transdermal distribution, particularly with regard to macromolecules. The microelectronics industry has produced microneedles in a range of dimensions, shapes, and polymers. The bulk of studies on drug delivery have concentrated on rigid microneedles, that have been shown in vitro to increase the skin's susceptibility to a range of substances including nanoparticles. Transdermal medication delivery can be improved by the use of microneedles. The present article discusses a wide range about microneedle variations and the ways they are manufactured. Microneedles that produce polymer provide an alternative. While soaking interstitial fluid instead of drugs, such innovative microneedles provide uninterrupted pathways among cutaneous microcirculation along with a connected patch-type reservoir. A few microneedles which have been officially approved for use in healthcare facilities by government bodies are also looked at. Additionally, it concentrates on the effective delivery of multiple medical chemicals via a variety of transporters, putting a special focus on the possible application employing microneedles within the transdermal approach.

Keywords: Transdermal drug delivery, Injection, Needles, Permeation, Skin, Systemic circulation.

INTRODUCTION

Injection using a painful hypodermic needle is the most common option when oral drug administration is not possible due to insufficient drug absorption or enzymatic breakdown in the digestive system or liver. To administer drugs via the skin and into the bloodstream in clinical practice, hypodermic needles are utilized. Clinically significant but uncomfortable are injections made with hypodermic needles. Additionally, they could cause bruising, soreness, and bleeding at the administration site, and in some situations, they carry a danger of contamination. Additional issues with their use include the risk of unintentional needle sticks and the requirement to educate medical personnel on how to use needles properly. [1]. Numerous methods have been investigated to increase skin permeability, including chemical and lipid enhancers [2, 3], electric fields used in iontophoresis and electroporation [4, 5], and pressure waves produced by ultrasound or photoacoustic effects [6, 7]. It has been discovered that 74% of currently available oral drugs are insufficiently effective to fulfil patients'

demands. When distributing the clinically needed quantity of drug through the skin to produce systemic impacts, attention need to be paid towards the skin's morphological, biophysical, physicochemical, and additional features [8]. Since a result, the transdermal medication delivery method has become a cutting-edge transporter in the most recent studies period [9] that solves both these attributes and the problems with traditional form of administration.

The idea of microneedles was first put forth in the 1970s [10], but it wasn't tested out experimentally until the 1990s, when the microelectronics industry gave the sector the microfabrication equipment required to create such tiny structures. Since the initial transdermal drug delivery studies in 1998 [11], there has been a rapidly rising interest in the field, with the majority of activity in the microfabrication community to develop new needle fabrication technologies and the drug delivery industry to develop microneedles for pharmaceutical applications. Microneedles are becoming more and more popular to boost the transdermal delivery of small and big molecules. Over the last few decades, educational

institutions and pharmaceutical enterprises have developed microneedles roughly the same time that microfabrication techniques for producing them have advanced [12–15]. To increase medicine conveyance over the skin, transdermal microneedles enlarge pores on the surface to a diameter of microns [13,15]. The major focus about the current study emphasises the use of microneedles as an experimental approach enabling transdermal drug delivery which considerably enhances the results associated with medication ingestion through transdermal channel [16-17].

DELIVERY OF MEDICATIONS THROUGH TRANSDERMAL NEEDLES

The majority of research has been on creating minuscule skin holes with silicon or metal microneedles. The "poke with patch" method makes holes in the skin with microneedles, then covers them with a transdermal patch (or a prototype). If an electric field is provided, iontophoresis or diffusion may take place. Another strategy is called "coat and poke," in which the needles are initially covered in

medication before being placed into the skin. A procedure which acts more akin to an insertion rather than an incision has also been used to study hollow microneedle designs and processes. Cylindrical needles allow effective fluid flow down the shaft of the needle through the skin, while being a greater challenge to produce and use. This can lead to much quicker times for management which can be modified gradually.

CLASSES OF MICRONEEDLES

Hollow, solid, coated, and polymer microneedles can be categorised into four groups (Figure 1) [18]. Compared to conventional hypodermic needles, hollow microneedles are shorter. Such substance that is liquid medicinal product is injected using wells within Microneedles. The skin is punctured with solid microneedles. A patch is then put on after that. Microneedles (MN) that have been drug coated are known as coated MNs, whereas microneedles consisting of polymers that create hydrogels are known as polymer MNs.




Figure no. -1 Different types of microneedles: solid, coated, dissolving and hollow from [19]

Hollow microneedles

Hollow microneedles have hollow bores at their centres. The device's shallow drilled, whenever placed underneath skin, creates an immediate passage towards the remaining lowermost layers beneath the epidermis without passing through the stratum corneum region underlying the skin. The majority of the time, these microneedles are utilised to inject skin-nearby medicinal solutions [21]. These are extremely costly to produce and need pricy micro production techniques [20]. These small needles contain a hollow bore that enables the faster diffusion through the interior of well-defined needles or pressure-driven flow of drugs. Drugs can be supplied inside of well-defined microneedles at either slower or quicker rates depending on pressure-driven flow or diffusion. Despite the creation of multiple vacuous microneedles, inadequate research evaluating how they could be utilised in the transport of chemicals inside skin is being undertaken. The aforementioned needles originated with a tiny pipette extractor and beveler, having an outer curvature of 60 Am, as well as penetrated entering the skin among 500 or 800 Am. This study illustrates

medication injection into the skin using microneedles. A commercially available 30 gauge hypodermic needle can be used to create hollow microneedles [23]. In HM, pressure may be adjusted to vary the flow rate, enabling quick bolus injection, gradual infusion, or variable delivery rates [22]. Additionally, a higher dosage of the medication solution may be administered via HM [14]. Hollow microneedles made of 30G stainless steel needles are manufactured [23]. A polyetheretherketone mould with holes in a 4 4 pattern was drilled (diameter: 9 mm). After that, needles with specified lengths of 300, 550, 700, and 900 m were inserted into the perforations.

Solid microneedles

To improve cellular absorption of molecules and gene transfection, these needles were introduced into nematodes and cells. Microneedles for transdermal administration applications that have been demonstrated to penetrate skin were created not long after this study was published. Hollow microneedles have a collection of protrusions which can be utilised to pierce the outermost layer of the skin prior to injecting a treatment as well as remove the later.

The aforementioned successfully transform the skin towards an opaque layer having micron-sized holes which enable medication molecules to get inside easily [20]. Needles are inserted into the skin for a predetermined amount of time to utilise them. Drug transfer into the viable epidermis is facilitated by the creation of microchannels by the use of microneedles. By coating with the medicine and inserting into the skin, solid microneedles can be made. The medicine will stay deposited inside the skin membranes after the removal of the microneedle carrying device. When placed under the skin, erodible microneedles disintegrate and make it simple to load drugs into them [24]. These tiny needles have the ability to puncture the top layers of skin, allowing for medication administration. Additionally, it has significant drawbacks. For instance, in solid microneedle arrays, the medicine given cannot readily pass through the skin's perforations because the microneedles keep them blocked. It was determined that applying a thick coating of drug formulation was not ideal since it lessened the microneedles' sharpness and made insertion more uncomfortable and challenging. These tiny needles may limit drug leakage, improving drug delivery effectiveness and opening the door to the introduction of several medicines [29].




Figure 2. Solid microneedles fabricated from silicon, metal and polymer

The microneedles were effectively introduced into the epidermis of a pig, and progressive dissolution was observed at 0, 60, 120, and 180 s [30]. The microneedles effectively penetrated pig skin while carrying methylene blue as a model medication [30]. The microneedles were effectively introduced into the epidermis of a pig, and progressive dissolution was observed at 0, 60, 120, and 180 s [30]. The microneedles effectively penetrated pig skin while carrying methylene blue as a model medication [30]. A microneedle roller is a tool that rolls across the skin and has MN placed on a cylindrical surface [18].

In this case, microneedles may be rolled across the skin since they are positioned on a cylindrical surface. Vertical static Franz diffusion cells were used in in vitro tests on pig ear skin that had undergone microneedling. Control was passive diffusion across untreated porcine skin. For 12 hours, aliquots were obtained every two hours and analysed using liquid chromatography-mass spectrometry. Captopril and metoprolol tartrate were delivered over pig skin using stainless steel microneedle arrays (750 m) produced by Microneedle Systems. We investigated how these medicines' diffusion was impacted by microneedle rollers [31]. Vaccine delivery using solid microneedles is also promising. Contrary to intramuscular administration, microneedle-mediated vaccination can result in more powerful and long-lasting antibody responses [12].

Coated microneedles

Coated microneedles are those that have a coating of a drug-containment dispersion. In the literature, a wide range of methods have been employed to make coated microneedles. A method for creating smart microneedle coatings that uses electrohydrodynamic atomization (EHDA) principles has been documented in the literature [32]. An ethanol:methanol (50:50) vehicular matrix was used to perform the EHDA spraying setup with metallic microneedles that ranged in altitude from 600 to 900 m linked to a neutral conductor via various accumulation intervals and collecting methods. These researchers used this technique to make medical films having tiny particles or micrometer-scales [32]. The remaining coating formulation ingredients were polyvinylpyrrolidone (PVP, polymer matrix system) and fluorescein dye (possible pharmacological, sensory, or disease status indicators). Relying upon these additives and wrapping modification processes, fragments as well as filaments with diameters between 100 nm to 3 m and 400 nm to 1 m had been effectively covered on microneedles in a controlled as well as specific way [32]. Ma and Gill used a polypropylene glycol matrices comprising the medicine lidocaine, which is resistant in liquid, to encase rigid microneedles [33]. homogenous coverings have been achieved over microneedle edges.

Dissolving microneedles

These consist of the patient-friendly one-step application process. The "poke and release" technique is the foundation upon which dissolving microneedles are created. They are created using polymers such as polysaccharides. After application and breakdown, these microneedles deliver the medicine that is enclosed in them into the skin. The preferred method of manufacturing dissolving microneedles is micromolding. Molecules tend to be filled by medicament and additive mixtures prior becoming gently air-dried since many medicines and immunisations are thermolabile. The manufacturing method involves putting a polymeric mixture into female mouldings, forming the container's microcavities with tension or the absence of air, draining below normal circumstances, spinning, or strain, as well as additional steps [34–36].

INSERTION OF A MICRONEEDLE INTO THE SKIN: MECHANICS [37]

The physical aspects of microneedle insertion, while receiving little attention, are essential for practical applications. Skin penetration requires microneedles with certain physical and geometrical properties. Others, as already mentioned, gain from high-velocity insertion whereas certain needle designs may simply be inserted by hand. When there is insufficient power, needles may break or bend before insertion. Individual microneedles were placed into the skin of human volunteers while the force as well as the displacement of the introduced needle was being measured. Skin resistance was utilised to determine if the needle had successfully entered the skin. The area of the needle tip had a close correlation with the insertion forces, which varied about 0.1 to 3.0 N (i.e., 10-300 g).

It was found that wall thickness had no effect on the degree of force required to insert solid and hollow needles with identical outer tip radii. Almost all of the devices under examination had margins of safety that were higher than one, and some of them were even considerably higher. The sterilised needles with the

largest margin of safety feature a thick wall for strength and a narrow tip radius for simplicity in insertion.

IMPAIRMENT CAUSED BY MICRONEEDLES [38]

In particular, the potential of painless medication delivery makes microneedles intriguing. Skin anatomy makes it possible to penetrate needles through the stratum corneum without activating nerves since the stratum corneum barrier of the skin is nerveless. There is no proof that microneedles can penetrate the living epidermis, where nerves are located; with barely a 10 to 20 am penetration through the stratum corneum in current practise. Microneedles, as previously indicated, being subsequently inserted, no less than through the outer layer of skin probably sporadically through the outermost dermis. Despite this, microneedles remain considered to be harmless. This is probably as a result of the size that they are, minimising the possibility that these needles could irritate an organ or make it uncomfortable.

FORMULATION DESIGN ELEMENTS [39]

The ability of microneedles to penetrate skin without breaking is one of the general design criteria that should be taken into account while creating new ones. It is important to choose polymers with enough mechanical strength and biocompatibility. They shouldn't cause any discomfort. The shape of the microneedle is also crucial, and the sharpness of the tip has a significant impact on how easily it can penetrate skin.

CONTROLLED DRUG RELEASE

The regulated amount of medicine should be administered via the microneedles at a certain, planned rate.

Penetration

The medicine should be able to penetrate the bodily tissues with the necessary depth using the tiny needles. By gently pressing with around 10 Newton strengths, it is possible to put tiny needles into the skin without feeling any pain.

Ruggedness

Develop microneedles that can penetrate the skin deeply without snapping. If they are excessively lengthy, the upper section of the microneedles may not have adequate stiffness and may shatter before penetration, thus they should be made to the ideal size. Without delaminating or breaking, they must be able to endure the insertion force.

SIZE OF MICRONEEDLES

Depending on the kind, different microneedles have different sizes. An average microneedle's length, base width, and tip diameter may be between 150 and 1500 microns, respectively. Microneedle tips come in a variety of designs, including triangles, rounded points, and arrows. The hollow microneedle arrays have lumen diameters of 30 micrometres and heights of 250 micrometres. A hollow microneedle array with a 150 mm center-to-center distance and a 10 m distance between the axis of the lumen and the outer column axis is constructed.

RESOURCES USED IN CONSTRUCTION

For the creation about microneedles, materials like transparent material, fragile rubber, elements involving stainless steel, pure gold over zinc, palladium, which cobalt, among and platinum as well, as well as polymers that decompose are required.

MICRONEEDLES' BENEFITS

The capacity to create them and their simplicity in penetrating the stratum corneum are only two advantages microneedles have over traditional needles. Decreases the likelihood of suffering from illness or damage. To continually administer medications into the body, arrangements of cylindrical syringes containing either simple absorption or a pump-like technology may be utilised. By retaining the medications in a tiny, carefully regulated consumption, these gadgets offer highly precise dosage, complicated release trends, administration locally, and an enhancement in the metabolic safety of the pharmaceuticals [47]. Additionally, they may administer drugs to certain cells with extreme precision.




Figure No 3: Different Penetration-Enhancing Techniques for Better Transdermal Drug Delivery [40]

MICRONEEDLE EVALUATION VARIABLES

Microneedle in-vitro research

Microneedles are used for in vitro testing in a variety of media, including agarose gel and methanol. To ascertain the properties of a novel testing substance or gadget, in vitro tests are utilised. The main goals of microneedle in vitro testing include optimising the microneedles, determining the penetration force and bending force, assessing the microneedle's strength, calculating the coating material's rate of dissolution, and estimating the effectiveness of drug delivery.

Method 1

The delivery effectiveness of the microneedles was evaluated in vitro. In this test, black ink is injected into the methanol-containing petridish using tiny needles that are integrated with a paradimethylsiloxane (PDMS) biochip. For this, isosceles and right triangle microneedles with 8.5 and 15 and 9.5 and 30 tip taper angles, respectively, have been employed [41].

Method 2

In order to assess the solution's penetration and flow into the 1% agarose gel, the diluted Rhodamine B dye is injected through microneedles into the gel [41].

Method 3

This approach evaluates the effects of inserting microneedles into porcine and pig corpse skin for 10–20 s and 5 minutes, respectively. The delivery effectiveness and dissolution rate of the coated substance, which is coated on the microneedle tip and coated with vitamin B, calcein, or sulforhodamine, are tested using this technique [41].

In vivo testing of microneedles

Preclinical in vivo studies frequently employ mice, rabbits, guinea pigs, monkeys, and other creatures. To assess the negative effects as well as security of the medicine being evaluated, in vivo testing's primary goal is. The main goals of the in vivo testing of microneedles are to perform skin toxicity tests, determine the penetration force through various skin types, mechanical stability, and bending breakage forces, carry out numerous non-clinical

safety studies and pharmacological studies, and determine multiple factors that include the immunogenicity of genotoxicity, skin sensitization, and allergization.

Method 1

In order to assess the effectiveness of microneedles, hairless mice's tail veins were punctured. It is utilised to calculate the microneedle's force of entry into the skin [41].

Method 2

To verify the effectiveness of the microneedles in vivo, Rhodamine B is administered intravenously into the tail of a laboratory mouse while the animal is sedated..

Method 3

Utilising microneedles to administer vaccines has been tested using this technique. With the use of solid metal microneedles, this approach administers ovaalbumin, a model protein antigen, to hairless guinea pigs at a rate of 20 g every 5s to 80 g [42].

MICRONEEDLE-BASED DRUG TRANSPORT

To give medications with microneedles, there are two main techniques: the poke technique and the poke with patch or coat. Microneedles coated with a dry-film antigen were injected into the skin of hairless guinea pigs in real time using a high-velocity injector. The largest insertion depth was discovered to be 300 Am, averaging 100 Am. By altering the volume of antigen solution deposited upon the needles along with the number of needles utilised, multiple doses may be administered. In the incision with patch procedure, tiny needles are used to create tiny holes within the skin beginning at first, then after they are taken out, a drug is put to the skin. Instead of using the coat-and-poke technique, wherein wraps the drug across the microneedle's exterior while injecting it into the skin? Therefore, the needles' area will serve as the means by which medications are spread [43]. This led to the development of plunge wrapping, which totally immerses tiny objects within the solution used for coating so it covers them [20]. Around the micrometre size, friction takes over. Some needles could be implanted easily via the aid of the hand, whereas others involve quick, forceful action [44].

Table1: Various medications are delivered using various transdermal carriers

DRUG	THERAPEUTIC CATEGORY	CARRIER	CONCLUSION
Ketoconazole	Anti-fungal	Ethosomes	A greater transdermal permeability [17]
Clotrimazole	Anti-fungal	Ethosomes	improved dermal delivery with greater effectiveness [19]
Ketoconazole	Anti-fungal	Ethosomes	Improved efficacy in the treatment of dermatological infections [24]
Bleomycin	Anticancer	Electroporation	the tumour is effectively treated with electrical pulses [25]
5-fluorouracil	Antineoplastic	Prodrug	25 techniques increased permeability [26]
Diclofenac	NSAID	Iontophoretic	One hour to reach the effective plasma concentration.[29]
Salbutamol	Bronchodilator	Iontophoretic	Enhanced transdermal flux [31]
Betamethasone-17-benzoate	Anti-inflammatory	Chemical stimulant	In vivo bioavailability that is improved [26]

DEVELOPMENTS IN DRUGS DELIVERY

The needles have been altered by being downsized to a micron size in an effort to increase patient compliance and safety. Given that a microneedle is a device used at the micron size, it should be able to administer the drug without triggering any discomfort or requiring

specific training. A microneedle's exact regional specificity of conveyance allows to get to areas including the cell centre, the suprachoroidal region in the eye, even the epidermis. The majority of microneedle approaches are being studied thus far in relation to cutaneous medication and vaccine delivery.. The barrier nature of the stratum corneum limits the use of traditional transdermal drug

delivery techniques. Experiments on improving pores in the skin have utilised a variety of psychological, behavioural, and physical strategies. For the administration of bio polymers such as insulin, hormones that stimulate expansion, immunobiologicals, amino acids, and peptides as microneedles might be manufactured as an

affordable overlay which is simple for clients to place on [22]. Numerous cosmeceuticals, as well as microneedles, which have generated a great deal of attention in the cosmetics sector, have been used to treat skin conditions such as acne shading, lines and scars, and skin tone [45].

Table 2: Microneedle applications for effective transdermal medication delivery [56, 58]

Drug	Transdermal system	Application
Anti restenosis	Micro needle patches	medication administration with specificity for atherosclerosis
Insulin	Microneedles	Increased percutaneous administration of insulin
Immunization (Antigen)	Microneedle array patch system	Effective immunization
Lidocaine Hydrochloride	Microneedle array	penetration that is consistent and powerful across the epidermis and stratum corneum
Recombinant Human Insulin	Microneedles hydrogel patch	long-lasting insulin release

CONCLUSION

Several alternative manufacturing procedures may be used to manufacture microneedles, which can then be created in a variety of sizes, shapes, and materials, according to a review of the literature. Porous microneedles have been investigated and shown to improve transdermal distribution when applied to the skin via the "dip and scrape," "coat along with poke," along with "poke with patch" methods. The use of microneedles, primarily as a part of a patch as well as an array, to effectively transport a variety of macromolecular drugs has been found to be possible. Multiple investigations indicate that the best delivery method is microneedling since it is effortless, efficient, and risk-free while also improving the medicine's management completely within the circulatory system. Over the upcoming years, it is anticipated that these risk-free methods would rank among the many crucial tools for regulated medication supply. This led it to the conclusion that, compared to earlier needle-based compositions for transdermal distribution, it was a stronger resistor. It has been demonstrated to inject small amounts of fluid into the skin. It is usually accepted that the diameter of the microneedle increases the possibility of activating painful receptors in the derma. Nevertheless there currently remains work to be conducted beforehand microneedles are often employed as ways to deliver medications in clinical treatment, the future prospects for the implementation of these medical devices is optimistic despite the aforementioned restrictions.

REFERENCES

1. Lhernould, M. S., Deleers, M., & Delchambre, A. (2015). Hollow polymer microneedles array resistance and insertion tests. *International journal of pharmaceutics*, 480(1-2), 152-157.
2. Barry, B., & Williams, A. (2003). Penetration enhancers. *Adv Drug Deliv Rev*, 56, 603-618.
3. Cevc, G. (2004). Lipid vesicles and other colloids as drug carriers on the skin. *Advanced drug delivery reviews*, 56(5), 675-711.
4. Kalia Y, Guy R. Iontophoresis. *Adv. Drug Deliv. Rev.* (in press).
5. Denet, A. R., Vanbever, R., & Pr  at, V. (2004). Skin electroporation for transdermal and topical delivery. *Advanced drug delivery reviews*, 56(5), 659-674.
6. Doukas, A. G., & Kollias, N. (2004). Transdermal drug delivery with a pressure wave. *Advanced drug delivery reviews*, 56(5), 559-579.
7. Mitragotri, S., & Kost, J. (2004). Low-frequency sonophoresis: a review. *Advanced drug delivery reviews*, 56(5), 589-601.
8. Kumar, J. A., Pullakandam, N., Prabu, S. L., & Gopal, V. (2010). Transdermal drug delivery system: an overview. *Int J Pharm Sci Rev Res*, 3(2), 49-54.
9. Akhtar, N., & Pathak, K. (2012). Preclinical and clinical aspects of antimicrobial drugs delivered through ethosomal vesicles. *Anti-Infective Agents*, 10(1), 15-25.
10. Gerstel, M. S., & Place, V. A. (1976). Drug delivery device. US Patent No. 3964482.
11. Henry, S., McAllister, D. V., Allen, M. G., & Prausnitz, M. R. (1998). Microfabricated microneedles: a novel approach to transdermal drug delivery. *Journal of pharmaceutical sciences*, 87(8), 922-925.
12. Jacoby, E., Jarrahan, C., Hull, H. F., & Zehrung, D. (2015). Opportunities and challenges in delivering influenza vaccine by microneedle patch. *Vaccine*, 33(37), 4699-4704. doi:10.1016/j.vaccine.03.062
13. Olatunji, O., Das, D. B., Garland, M. J., Belaid, L. U. C., & Donnelly, R. F. (2013). Influence of array interspacing on the force required for successful microneedle skin penetration: theoretical and practical approaches. *Journal of pharmaceutical sciences*, 102(4), 1209-1221.
14. Cheung, K., Han, T., & Das, D. B. (2014). Effect of force of microneedle insertion on the permeability of insulin in

- skin. *Journal of diabetes science and technology*, 8(3), 444-452.
15. Kaur, M., Ita, K. B., Popova, I. E., Parikh, S. J., & Bair, D. A. (2014). Microneedle-assisted delivery of verapamil hydrochloride and amlodipine besylate. *European journal Of pharmaceuticals and biopharmaceutics*, 86(2), 284-291.
16. Sivamani, R. K., Liepmann, D., & Maibach, H. I. (2007). Microneedles and transdermal applications. *Expert opinion on drug delivery*, 4(1), 19-25.
17. Prausnitz, M. R., & Langer, R. (2008). Transdermal drug delivery. *Nature biotechnology*, 26(11), 1261-1268.
18. Jepps, O. G., Dancik, Y., Anissimov, Y. G., & Roberts, M. S. (2013). Modeling the human skin barrier—Towards a better understanding of dermal absorption. *Advanced drug delivery reviews*, 65(2), 152-168.
19. Kim, Y. C., Park, J. H., & Prausnitz, M. R. (2012). Microneedles for drug and vaccine delivery. *Advanced drug delivery reviews*, 64(14), 1547-1568.
20. Srinivas, P., Shanthi, C. L., & Sadanandam, M. S. (2010). Microneedles patches in drug delivery: a review. *Int J Pharm Tech*, 2(3), 329-344.
21. Vandervoort, J., & Ludwig, A. (2008). Microneedles for transdermal drug delivery: a minireview. *Frontiers in Bioscience-Landmark*, 13(5), 1711-1715.
22. Kim, Y. C., Park, J. H., & Prausnitz, M. R. (2012). Microneedles for drug and vaccine delivery. *Advanced drug delivery reviews*, 64(14), 1547-1568.
23. Verbaan, F. J., Bal, S. M., Van den Berg, D. J., Dijkman, J. A., Van Hecke, M., Verpoorten, H., ... & Bouwstra, J. A. (2008). Improved piercing of microneedle arrays in dermatomed human skin by an impact insertion method. *Journal of controlled release*, 128(1), 80-88.
24. Morrow, D. I. J., McCarron, P. A., Woolfson, A. D., & Donnelly, R. F. (2007). Innovative strategies for enhancing topical and transdermal drug delivery. *The Open Drug Delivery Journal*, 1(1).
25. Gupta, J., Gill, H. S., Andrews, S. N., & Prausnitz, M. R. (2011). Kinetics of skin resealing after insertion of microneedles in human subjects. *Journal of controlled release*, 154(2), 148-155.
26. Luo, Z., Ye, T., Ma, Y., Gill, H. S., & Nitin, N. (2013). Microprecision delivery of oligonucleotides in a 3D tissue model and its characterization using optical imaging. *Molecular Pharmaceutics*, 10(8), 2868-2879.
27. Vinayakumar, K. B., Hegde, G. M., Ramachandra, S. G., Nayak, M. M., Dinesh, N. S., & Rajanna, K. (2015). Development of cup shaped microneedle array for transdermal drug delivery. *Biointerphases*, 10(2).
28. Gill, H. S., & Prausnitz, M. R. (2007). Coated microneedles for transdermal delivery. *Journal of controlled release*, 117(2), 227-237.
29. Kim, M. C., Lee, J. W., Choi, H. J., Lee, Y. N., Hwang, H. S., Lee, J., ... & Kang, S. M. (2015). Microneedle patch delivery to the skin of virus-like particles containing heterologous M2e extracellular domains of influenza virus induces broad heterosubtypic cross-protection. *Journal of controlled release*, 210, 208-216.
30. Olatunji, O., Igwe, C. C., Ahmed, A. S., Alhassan, D. O., Asieba, G. O., & Diganta, B. D. (2014). Microneedles from fish scale biopolymer. *Journal of Applied Polymer Science*, 131(12). doi:10.1002/app.40377
31. T Nguyen, K., B Ita, K., J Parikh, S., E Popova, I., & A Bair, D. (2014). Transdermal delivery of captopril and metoprolol tartrate with microneedles. *Drug Delivery Letters*, 4(3), 236-243.
32. Khan, H., Mehta, P., Msallam, H., Armitage, D., & Ahmad, Z. (2014). Smart microneedle coatings for controlled delivery and biomedical analysis. *Journal of drug targeting*, 22(9), 790-795.
33. Ma, Y., & Gill, H. S. (2014). Coating Solid Dispersions on Microneedles via a Molten Dip-Coating Method: Development and In Vitro Evaluation for Transdermal Delivery of a Water-Insoluble Drug. *Journal of pharmaceutical sciences*, 103(11), 3621-3630.
34. Wang, Q., Yao, G., Dong, P., Gong, Z., Li, G., Zhang, K., & Wu, C. (2015). Investigation on fabrication process of dissolving microneedle arrays to improve effective needle drug distribution. *European Journal of Pharmaceutical Sciences*, 66, 148-156.
35. Sullivan, S. P., Koutsonanos, D. G., del Pilar Martin, M., Lee, J. W., Zarnitsyn, V., Choi, S. O., ... & Prausnitz, M. R. (2010). Dissolving polymer microneedle patches for influenza vaccination. *Nature medicine*, 16(8), 915-920.
36. Hong, X., Wei, L., Wu, F., Wu, Z., Chen, L., Liu, Z., & Yuan, W. (2013). Dissolving and biodegradable microneedle technologies for transdermal sustained delivery of drug and vaccine. *Drug design, development and therapy*, 945-952.
37. Davis, S. P., Landis, B. J., Adams, Z. H., Allen, M. G., & Prausnitz, M. R. (2004). Insertion of microneedles into skin: measurement and prediction of insertion force and needle fracture force. *Journal of biomechanics*, 37(8), 1155-1163.
38. Kaushik, S., Hord, A. H., Denson, D. D., McAllister, D. V., Smitra, S., Allen, M. G., & Prausnitz, M. R. (2001). Lack of

- pain associated with microfabricated microneedles. *Anesthesia & Analgesia*, 92(2), 502-504.
39. Gandhi, K., Monika, A. D., Kaira, T., & Singh, K. (2012). Transdermal drug delivery: A Review. *Inter. J. Res. Pharm. Sci*, 3, 379-388.
40. Dhamecha, D. L., Rathi, A. A., Saifee, M., Lahoti, S. R., & Dehghan, M. H. G. (2009). Drug vehicle based approaches of penetration enhancement. *Int J Pharm Pharm Sci*, 1(1), 24-46.
41. Paik, S. J., Lim, J. M., Jung, I., Park, Y., Byun, S., Chung, S., ... & Cho, D. D. (2003, June). A novel microneedle array integrated with a PDMS biochip for microfluid systems. In *TRANSDUCERS'03. 12th International Conference on Solid-State Sensors, Actuators and Microsystems. Digest of Technical Papers (Cat. No. 03TH8664)* (Vol. 2, pp. 1446-1449). IEEE.
42. Smith EW, Maibach HI. (2006) The textbook of Percutaneous Penetration Enhancers. 2nd ed;
43. Kapoor, D., Patel, M., & Singhal, M. (2011). Innovations in Transdermal drug delivery system. *International Pharmaceutical Science*, 1(1), 54-61.
44. Prausnitz, M. R., Mitragotri, S., & Langer, R. (2004). Current status and future potential of transdermal drug delivery. *Nature reviews Drug discovery*, 3(2), 115-124.
45. Bariya, S. H., Gohel, M. C., Mehta, T. A., & Sharma, O. P. (2012). Microneedles: an emerging transdermal drug delivery system. *Journal of Pharmacy and Pharmacology*, 64(1), 11-29.
46. Sheer, A., & Chauhan, M. (2011). Ethosomes as vesicular carrier for enhanced transdermal delivery of Ketoconazole-Formulation and Evaluation. *IJPIs J. Pharm. Cosmetol*, 1(3), 1-14.
47. Samnani, A., Shahwal, V., Bhowmick, M., Joshi, A., & Dubey, B. K. (2012). Design and evaluation of ultradeformable soft elastic nano vesicle ethosomes for dermal delivery. *Int J Biomed Adv Res*, 3(02), 111-7.
48. Rasheed, S. H., Tirumoorthy, N., & Kundlik, G. (2007). Enhanced transdermal delivery of ketoconazole via ethosomes formulation and evaluation. *World J Pharm Pharm Sci*, 1(1), 238-49.
49. Banga, A. K., & Prausnitz, M. R. (1998). Assessing the potential of skin electroporation for the delivery of protein- and gene-based drugs. *Trends in biotechnology*, 16(10), 408-412.
50. Barry, B. W., Southwell, D., & Woodford, R. (1984). Optimization of bioavailability of topical steroids: penetration enhancers under occlusion. *Journal of investigative dermatology*, 82(1), 49-52.
51. Byl, N. N. (1995). The use of ultrasound as an enhancer for transcutaneous drug delivery: phonophoresis. *Physical therapy*, 75(6), 539-553.
52. Hui, X., Anigbogu, A., Singh, P., Xiong, G., Poblete, N., Liu, P., & Maibach, H. I. (2001). Pharmacokinetic and local tissue disposition of [14C] sodium diclofenac following iontophoresis and systemic administration in rabbits. *Journal of pharmaceutical sciences*, 90(9), 1269-1276.
53. Nolan, L. M. A., Corish, J., Corrigan, O. I., & Fitzpatrick, D. (2003). Iontophoretic and chemical enhancement of drug delivery: Part I: Across artificial membranes. *International journal of pharmaceutics*, 257(1-2), 41-55.
54. McAllister, D. V., Allen, M. G., & Prausnitz, M. R. (2000). Microfabricated microneedles for gene and drug delivery. *Annual review of biomedical engineering*, 2(1), 289-313.
55. Alarcon, J. B., Hartley, A. W., Harvey, N. G., & Mikszta, J. A. (2007). Preclinical evaluation of microneedle technology for intradermal delivery of influenza vaccines. *Clinical and Vaccine Immunology*, 14(4), 375-381.
56. Duan, D., Moeckly, C., Gysbers, J., Novak, C., Prochnow, G., Siebenaler, K., ... & Hansen, K. (2011). Enhanced delivery of topically-applied formulations following skin pre-treatment with a hand-applied, plastic microneedle array. *Current drug delivery*, 8(5), 557-565.
57. Qiu, Y., Qin, G., Zhang, S., Wu, Y., Xu, B., & Gao, Y. (2012). Novel lyophilized hydrogel patches for convenient and effective administration of microneedle-mediated insulin delivery. *International journal of pharmaceutics*, 437(1-2), 51-56.
58. Ito, Y., Hagiwara, E., Saeki, A., Sugioka, N., & Takada, K. (2006). Feasibility of microneedles for percutaneous absorption of insulin. *European Journal of pharmaceutical sciences*, 29(1), 82-88.